



TRON

L U B R I C A N T S

 **ULTRON**

 **MEGATRON**

 **POWERTRON**

Technical Data Sheet

Megatron Mould Release Oil

Applications and Preparation

Megatron Mould Release Oil is recommended as a non-staining concrete release agent that provides exceptional releasing properties. It is applied neat as a coating on the insides of mould surfaces and shutters to be filled with cement or concrete. Incorporated in the blend are special additives to ensure smooth release and finishes on a wide variety of manufacturing and building applications. It is compatible with Non-absorbent materials, aluminium, steel and fibreglass.

Surfaces should be clean before application. Remove previous build-up of concrete, rust, scale and dirt. **DO NOT DILUTE.** It may be applied by brush, roller, spray or dripping on forms immediately before pouring concrete. Must be kept off reinforcing steel. Estimated coverage up to 60m² per litre depending porosity.

Benefits

- Ensures a clean, smooth finish.
- Enables quick, easy removal from the mould.
- Good anti-rust properties (for steel moulds).
- Good spray ability and mould wetting capability.

Typical Physical Characteristics

Megatron Mould Release Oil	
Viscosity, cSt @ 40°C	19
Density, 20°C, kg/l	0.8467
Flash Point, °C	75
Pour Point, °C	-16

The values of the specifications shown in this table are typical values given as an indication only.

Pack Sizes

- 500 ml ,1 Litre, 5 Litre and 20 Litre Plastic Bottles
- 208 Litre Steel Drums
- 1000 Litre IBC

Health and Safety Information

For recommendations on safe handling and use of this product, please refer to the Material Safety Data sheet available on www.tronlubricants.com

Misrepresentation Act 1967. Trade description Act 1968. The information in this publication is based on our experience and reports from customers. There are many factors outside our control and knowledge which effect the use and performance of our products for which reason no warranty is given, express or implied. This information sheet was prepared from the best information available at the time of issue. While the values and characteristics are considered representative, some variation, not affecting performance, can be expected. It is the responsibility of the user to ensure that the products are used in the applications for which they are intended.